

SIMPLY MODERN

- Concrete Inspired • Wall, floors
- Residential + light commercial



Coffee

12" x 12" ☒
 12" x 24" ☒
 3" x 12" BN ☒
 6" x 12" Cove Base ☒
 2" x 2" Mos ☒

Black

12" x 12" ☒
 12" x 24" ☒
 3" x 12" BN ☒
 6" x 12" Cove Base ☒
 2" x 2" Mos ☒

Creme

12" x 12" ☒
 12" x 24" ☒
 3" x 12" BN ☒
 6" x 12" Cove Base ☒
 2" x 2" Mos ☒

Grey

12" x 12" ☒
 12" x 24" ☒
 3" x 12" BN ☒
 6" x 12" Cove Base ☒
 2" x 2" Mos ☒

Tan

12" x 12" ☒
 12" x 24" ☒
 3" x 12" BN ☒
 6" x 12" Cove Base ☒
 2" x 2" Mos ☒



Grey



Black

☒ In stock

Images are for reference only; please refer to live product for an accurate color representation.

ROBERT F. HENRY
TILE COMPANY
 EST. 1933

SIMPLY MODERN



Creme and Tan



Coffee

☒ In stock

Images are for reference only; please refer to live product for an accurate color representation.

ROBERT F. HENRY
TILE COMPANY
EST. 1933

Physical Properties	ASTM Test	Industry Standards	Stonepeak Results
Water Absorption	C373	Impervious < 0.5 %	≤ 0.1%
Thickness Dimension	C499	Range ± 0.04 Inc. Max	≤ ± 0.04 Inch
Facial Dimension	C499	± 0.25%	≤ ± 0.25%
Warpage Average Diagonal	C485	Range - 0.30% /+ 0.40%	≤ ± 0.40%
Warpage Average edge	C485	Range - 0.30% /+ 0.40%	≤ ± 0.40%
Wedging	C502	± 0.25%	≤ ± 0.25%
Bond Strength	C482	≥ 50 psi	≥ 200 psi
Breaking Strength	C648	≥ 250 lbf	≥ 400 lbf
Hardness (Mohs)	C1895	Range 0 - 10	≥ 7
Visible Abrasion Resistance for Glazed ties	C1027	No Requirement; Range 0 - 5	Class IV
Frost Resistance	C1026	No sample must show alterations to surface	No evidence of Damage
Chemical Resistance	C650	No Requirement; Range E - A	Class A / Unaffected
Stain Resistance	C1378	No Requirement; Range E. A	Class A
DCOF*	ANSI A 326.3	≥ 0.42	≥ 0.55*
Aesthetic Class/Shade Rating	Visual Evaluation Shade & Texture	No Requirement; Range V0 - V4	V2